

# SAFRA Si5/4043

#### **DESCRIPTION**

Aluminium wires and rods for welding alloys with maximum 2% alloying elements and for aluminium alloys containing up to 7% of Si. Excellent flowability and penetration characteristics. Applications in the construction sector and in the automotive industry.

**AWS A5.10/A5.10M** ER4043A,R4043A

**EN ISO 18273** S Al 4043A / AlSi5(A)

#### **MATERIALS TO BE WELDED**

Al Si 5 / Al Mg Si 0,5 / Al Mg Si 0,8 / Al Mg Si 1 / Al Zn Mg / Al Cu Mg /

(after anodizing welding will be of a dark grey colour)

# SHIELDING GASES FOR GMAW/GTAW

<u>l1, l2, l3</u>

# MINIMAL VALUES OF THE MECHANICAL PROPERTIES (welded metal)

| Tensile strenght Rm:  | 120 N/mm² |
|-----------------------|-----------|
| Yeld strenght Rp 0,2: | 40 N/mm²  |
| Elongation L=5d:      | 8%        |

#### **AVAILABLE SIZES\***

### MIG: 5-6-7 Kg D300 or K300/KS300 spools

Diameter of the wire 1,0 mm - 1,2 mm - 1,6 mm - 2,0 mm - 2,4 mm

### TIG carton box of 10 Kg (x 1000 mm length)

Diameter of the rods 1,6 mm - 2,0 mm - 2,4 mm - 3,2 mm - 4,0 mm - 5,0 mm

## MINI-MIG: 0,5 Kg D100 spools / 2 Kg D200 spools

Diameter of the wire 1,00 mm - 1,2 mm - 1,6 mm

## \* More diameters and packaging upon request

## CHEMICAL COMPOSITION

in%(m/m)<sup>(a)</sup>

| Al | remainder            |
|----|----------------------|
| Si | 4,5 - 6,0            |
| Fe | 0,60                 |
| Cu | 0,30                 |
| Mn | 0,15                 |
| Mg | 0,20                 |
| Zn | 0,10                 |
| Ti | 0,15                 |
| Be | 0,0003               |
|    | others each<br>0,05  |
|    | others total<br>0,15 |

laj Single values shown in the table are maximum values, unless otherwise noted.

